

Econo Coat The non-reflective EconoCoat is the traditional glue coating window films, with IRISFILM special coatings on the polyester (PET), IRISFILM invites you to experience a whole new line of glue coating films with:

- * No more white spots
- * No more dust spots
- * No more reddish (purple colors when films are folded)
- * No more color wave lines
- * Wide color range to choose from
- * Choice of 1-Ply and 2-Ply constructions

Product Code	VLT%	UV%	IR%	SRC Rate	Layer	Thickness	Total Solar Energy Rejected
NR1BK02SRC	2	99.5	21	3H	1-Ply	38u(1.52mil)	56.5
NR1BK05SRC	5	96	19	3H	1-Ply	38u(1.52mil)	54
NR1BK10SRC	10	90	17	3H	1-Ply	38u(1.52mil)	50.6
NR1BK15SRC	15	85	19	3H	1-Ply	38u(1.52mil)	47.3
NR1BK35SRC	35	61	20	3H	1-Ply	38u(1.52mil)	40.6
NR1BK50SRC	50	45	19	3H	1-Ply	38u(1.52mil)	33.1
NR1CC05SRC	5	97	20	3H	1-Ply	38u(1.52mil)	54.6
NR1CC15SRC	15	86	19	3H	1-Ply	38u(1.52mil)	49.4
NR1CC35SRC	35	65	20	3H	1-Ply	38u(1.52mil)	40.7
NR1GF05SRC	5	96	19	3H	1-Ply	38u(1.52mil)	54
NR1GF10SRC	10	95	20	3H	1-Ply	38u(1.52mil)	52.4
NR1GF30SRC	30	64	18	3H	1-Ply	38u(1.52mil)	41.7
NR1OG05SRC	5	96	19	3H	1-Ply	38u(1.52mil)	54
NR1OG15SRC	15	92	19	3H	1-Ply	38u(1.52mil)	49.6
NR1OG35SRC	35	74	19	3H	1-Ply	38u(1.52mil)	40.4
NR1BR05SRC	5	99	18	3H	1-Ply	38u(1.52mil)	53.5
NR1BR15SRC	15	94	17	3H	1-Ply	38u(1.52mil)	48.6
NR1BR35SRC	35	74	19	3H	1-Ply	38u(1.52mil)	40.4
NR1GY05SRC	5	91	20	3H	1-Ply	38u(1.52mil)	54.4
NR1GY15SRC	15	80	20	3H	1-Ply	38u(1.52mil)	49.8
NR1GY35SRC	35	52	20	3H	1-Ply	38u(1.52mil)	40.3
NR1BL25SRC	25	75	19	3H	1-Ply	38u(1.52mil)	44.8
NR1BL60SRC	60	43	20	3H	1-Ply	38u(1.52mil)	29.3
NR1GN30SRC	30	87	21	3H	1-Ply	38u(1.52mil)	44.1
NR1GN65SRC	65	37	21	3H	1-Ply	38u(1.52mil)	27.5
NR1YL50SRC	50	89	21	3H	1-Ply	38u(1.52mil)	35.5
NR1RD20SRC	20	92	19	3H	1-Ply	38u(1.52mil)	47.4
NR2OG05SRC	5	99	16	3H	2-Ply	43u(1.72mil)	52.5
NR2OG20SRC	17	99	18	3H	2-Ply	43u(1.72mil)	48.4
NR2OG30SRC	30	93	15	3H	2-Ply	43u(1.72mil)	41

Terminology

T%: Transmittance Rate

R%: Reflectance + Absorptance Rate

IR: Infrared (Solar Heat) in spectrum range >700nm.

UV: Ultraviolet in spectrum range <400nm.

Visible Light: Spectrum range 401nm~699nm.

Specification Tolerance: ±5%.

SRC: Scratch Resistance Hardcoat.

IRISFILM Corp.

Taipei Regional Office

3F, No. 208, Shi-Tsang Road, Taipei City 10861, Taiwan R.O.C.

No. 69, Dinghu Road, Takang Gueishan Shiang,

Taoyuan County, 33378 Taiwan R.O.C.

Tel: +886-2-2302-3000 (Operator)

Sales Direct Line: +886.2.2336.7198

Fax: +886-2-2302-4000

E-mail: sales@irisfilm.com.tw

Web: <http://www.irisfilm.tw>

Business Hours 9:00 am ~ 6:00 pm (GMT + 8:00 Taipei Time)