



Infracut is IRISFILM's top of the line IR Cut series. High visible transmittance rate upto 75%, and high infrared (heat) resistance rate of upto 98%!

Product Code	VLT%	UV%	IR%	SRC Rate	Layer	Thickness	Note
IR4560	52	96	52	4H	2-ply	43u (1.72mil)	Reflective
IR4560YL	55	96	52	4H	2-ply	43u (1.72mil)	Reflective
IR4560RD	50	96	52	4H	2-ply	43u (1.72mil)	Reflective
IR4560BL	52	96	52	4H	2-ply	43u (1.72mil)	Reflective
IR4560PR	50	96	52	4H	2-ply	43u (1.72mil)	Reflective
IR4560GN	52	96	52	4H	2-ply	43u (1.72mil)	Reflective
IR6080	74	90	60	4H	1-ply	38u (1.52mil)	Non-Reflective
IR6080YL	70	90	60	4H	1-ply	38u (1.52mil)	Non-Reflective
IR6080RD	65	90	60	4H	1-ply	38u (1.52mil)	Non-Reflective
IR6080BL	65	90	60	4H	1-ply	38u (1.52mil)	Non-Reflective
IR7065	65	96	72	4H	2-ply	43u (1.72mil)	Non-Reflective
IR7065YL	60	96	75	4H	2-ply	43u (1.72mil)	Non-Reflective
IR7065RD	55	96	73	4H	2-ply	43u (1.72mil)	Non-Reflective
IR7065BL	55	96	74	4H	2-ply	43u (1.72mil)	Non-Reflective
IR7555	50	96	78	4H	2-ply	43u (1.72mil)	Reflective
IR7555YL	50	96	78	4H	2-ply	43u (1.72mil)	Reflective
IR7555RD	43	96	78	4H	2-ply	43u (1.72mil)	Reflective
IR7555BL	43	96	78	4H	2-ply	43u (1.72mil)	Reflective
IR9666	70	99	98	4H	2-ply	43u (1.72mil)	Reflective

Terminology

T%: Transmittance Rate

R%: Reflectance + Absorptance Rate

IR: Infrared (Solar Heat) in spectrum range >700nm.

UV: Ultraviolet in spectrum range <400nm.

Visible Light: Spectrum range 401nm~699nm.

Specification Tolerance: ±5%.

SRC: Scratch Resistance Hardcoat.

IRISFILM Corp.

Taipei Regional Office

3F, No. 208, Shi-Tsang Road, Taipei City 10861, Taiwan R.O.C.

No. 69, Dinghu Road, Takang Gueishan Shiang,

Taoyuan County, 33378 Taiwan R.O.C.

Tel: +886-2-2302-3000 (Operator)

Sales Direct Line: +886.2.2336.7198

Fax: +886-2-2302-4000

E-mail: sales@irisfilm.com.tw

Web: <http://www.irisfilm.tw>

Business Hours 9:00 am ~ 6:00 pm (GMT + 8:00 Taipei Time)